

Uniclass L6412	EPIC F32
Cl/SfB	Yq4

April 2006

One Coat Renders

Application Guide for Summer Months

EuroMix Dry Mortar System

1. Preparation

- Walls require a wetting down before application. This may be required the day before application and again on the day of application, in order to kill suction.
- The render should be protected from direct sunlight and wind with protective netting, which is attached to the scaffolding.

2. Application


- In sunny weather work has to commence on the shady side of the building continue around following the sun to prevent rapid drying.
- The render must be applied in two passes. The first to give a 5mm thick coating on the background. After 30 minutes a 2nd coat is to be applied to produce a total thickness of 18mm. The surface should be closed using a spatular to prevent water loss on the surface of the render.
- The material should be checked at regular intervals after application to ensure even coverage and consistency.

3. Curing

- The render must be protected from direct sunlight and wind after it is applied.
- If wawm weather is expected the render should be applied as late as possible in the afternoon so that curing takes place during the cooler part of the day and overnight.
- Same day application and finishing of is not recommended.



EuroMix



Helpline: **0845 850 9090** (UK) **01 630 2732** (Ireland)

Visit us at: **www.euromix.com**

E-mail: **info@cpieuromix.com**

